



BITUMEN

BITUMEN Penetration 60/70 TDS

60/70 Bitumen Analysis				
No	Specification	Unit	RESULT	Test Method
1	Specific Gravity	@25 °C	1.01-1.06	D-70
2	Penetration	@25 °C	60/70	D-5
3	Softening Point	°C	49/56	D-36
4	Ductility	@25 °C	100 Min	D-113
5	Loss on Heating	WT %	0.2 Max	D-6
6	Flash Point	°C	250 Min	D-92
7	Solubility in CS ₂	WT %	99.5 Min	D-4
8	Drop in Penetration after Heating	%	20 Max	D-5 & D-6
9	SPOT Test	-	NEGATIVE	A.A.S.H.O.T.102

Notes:

Datis Bitumen's Penetration is pure petroleum product. It manufactured from vacuum bottom by passing hot air. Furthermore, penetration between 60~70 desi-millimeter and softening point between 49~56C. It has a thermoplastic property that is like as synthetic resin material that gets softer with heating and hardens when cooled.



Datis Inc.

Reg. No.: 318496

Affiliated to Datis Export Group



Datis Export Group

YOU DESIRE, WE EXPORT

Follow US

On Social Networks



ONLINE on WhatsApp, Wechat, Telegram

+989123214280



INQUIRY and sending Letter of Intent (LOI)

Sales@Datis-inc.com



WWW.DATIS-INC.COM
SALES@DATIS-INC.COM

Tel: +98-21-460-92320
WhatsApp/Wechat: +989123214280