



LFI 2119

LFI 2119			
Properties	Value ⁽¹⁾	Unit	Test method
Physical Properties			
MFI (190 °C / 2 .16 Kg)	1.9	dg/min	ISO 1133
Density	921	Kg/m3	ISO 1183 (A)
Mechanical properties ⁽²⁾			
Impact strength	26	KJ/m	ASTM D 4272
Tear strength (TD)	25	KN/m	ISO 6383-2
Tear Strength (MD)	60	KN/m	ISO 6383-2
Yield stress (TD)	11	MPa	ISO 527
Yield stress (MD)	13	MPa	ISO 527
Tensile Stress at break (TD)	20	MPa	ISO 527
Tensile Stress at break (MD)	35	MPa	ISO 527
Strain at Break (TD)	>500	%	ISO 527
Strain at Break (MD)	>150	%	ISO 527
Modulus of Elasticity (TD)	200	MPa	ISO 527
Modulus of Elasticity (MD)	190	MPa	ISO 527
Coefficient of friction	>1		ASTM D 1894
Blocking	20	g	SABTEC method
Re-blocking	100	g	SABTEC method
Optical properties ⁽²⁾			
Haze	9	%	ASTM D 1003A
Gloss(45°)	55	%	ASTM D 2457
Clarity	26	mV	
<i>Additive : Antioxidant</i>			



➤ **Notes:**

(1) Typical Values: not to be construed as specifications limits.

(2) Properties are based on 25 µm blown film produced at a melt temperature of 170°C and 3 BUR using 100% Lfi 2119.

➤ **Product Description**

LFI2119 is a low density polyethylene, with excellent optical properties. This grade offers a high output and excellent draw down and specially designed for general purpose thin films.

➤ **Typical Application**

LFI2119 is recommended for blown film extrusion. This product is suitable for manufacture of general purpose LDPE film packaging and general lamination films.

➤ **General Information**

➤ Licensor: LFI2119 has been manufactured using SABTEC licensed technology.

➤ **Processing Conditions:**

Extruder temperature profile: 160-185°C Frost line height: 5-7 times die diameter. Blow Up Ratio: 2-3

Recommended film thickness: 20 to 50 µm

Please note that, these processing conditions are recommended by producer only for 100% LFI2119 resin (not in the case of blending with any other compatible material), but because of the many particular factors which are outside our knowledge and control, and may affect the use of product, no warranty is given.

➤ **Packaging**

Supplied in pellet form and can be packaged in 25kg Bags, one ton semi bulk or 17 tons bulk containers.

➤ **Food Packaging**

The above mentioned grade meets the relevant requirements of plastics directive 2002/72/EC (06-08-2002) and its amendments till



directive 2008/39EC relating to plastic materials and articles intended to come into contact with foodstuffs.

➤ **Pharmaceutical Application**

The above mentioned grade meets the requirements of the European pharmacopeia version 6 section 3.1.5 for pharmaceutical application.

➤ **Conveying**

Conveying equipment should be designed to prevent accumulation of fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used:

1. Be equipped with adequate filters.
2. Is operated and maintained in such a manner to ensure no leaks develop.
3. That adequate grounding exists at all times.

We further recommend that good housekeeping will practiced throughout the facility.

➤ **Storage**

All resins should be protected from direct sunlight and/or heat during storage. The storage location should also be dry, dust free and the ambient temperature should not exceed 50°C. It is also advisable to process polyethylene resins (in pelletized or powder form) within 6 months after delivery, this because also excessive aging of polyethylene can lead to a deterioration in quality. We would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is also advisable to process polyethylene resins (in pelletized or powder form) within 6 months after delivery, this because also excessive aging of polyethylene can lead to a deterioration in quality.

➤ **Handling**

Minimal protection to prevent possible mechanical or thermal injury to the eyes. Fabrication areas should be ventilated to carry away fumes or vapors.

➤ **Combustibility**

Polyethylene resins will burn when supplied adequate heat and oxygen. They should be handled and stored away from contact with direct flames and/or other ignition sources .in burning; polyethylene resins contribute high heat and may generate a dense black smoke. Fires can be extinguished by conventional means with water and mist preferred. In enclosed areas, fire fighters should be provided with self-contained breathing apparatus.

➤ **LD Polyethylene**

LDPE Low Density Polyethylene (LDPE) for production of such goods as film, bags, disposable containers , Agriculture, flexible injection parts , toys , home appliances, covers , As the base resin masterbatches , Laundry transparent bag production and zipper bags



Datis Inc.

Reg. No.: 318496

Affiliated to Datis Export Group



You Desire, We Export

Datis Export Group

YOU DESIRE, WE EXPORT

Follow US

On Social Networks



ONLINE on WhatsApp, Wechat, Telegram

+989123214280



INQUIRY and sending Letter of Intent (LOI)

Sales@Datis-inc.com



WWW.DATIS-INC.COM

SALES@DATIS-INC.COM

Tel: +98-21-460-92320

WhatsApp/Wechat: +989123214280