



CLINKER

Product	Portland Cement CLINKER Type 2
Standard	ASTM C-150, ISIRI 389

ORDINARY PORTLAND CEMENT CLINKER			
Standard: ASTM C-150 – TYPE II			
No	Chemical Analysis	PARAMETER	Results Obtained
1	Silicon Dioxide	% SiO ₂	21.60
2	Aluminum Oxide	% AL ₂ O ₃	4.94
3	Ferric Oxide	% FE ₂ O ₃	3.42
4	Calcium Oxide	% CAO	64.10
5	Magnesium Oxide	% MGO	4.10
6	Sulfur Trioxide	% SO ₃	0.48
7	Potassium oxide	% K ₂ O	0.69
8	Sodium Oxide	% Na ₂ O	0.28
9	Loss of Ignition	% L.O.I	0.22
10	Lime Saturated Factor	L.S.F	93.53
11	Silica Modulus	S.I.M	2.58
12	Alumina Modulus	A.L.M	1.44
13	Tricalcium Silicate	%C ₃ S	57.30
14	Decalcium Silicate	%C ₂ S	18.70
15	Tricalcium Aluminate	%C ₃ A	7.30
16	Tetra Calcium Alumina Ferrite	%C ₄ AF	10.41
17	Free Lime	%	1.00

Datis Inc.

Reg. No.: 318496

Affiliated to Datis Export Group



You Desire, We Export

Datis Export Group

YOU DESIRE, WE EXPORT

Follow US

On Social Networks



ONLINE on WhatsApp, Wechat, Telegram

+989123214280



INQUIRY and sending Letter of Intent (LOI)

Sales@Datis-inc.com



WWW.DATIS-INC.COM
SALES@DATIS-INC.COM

Tel: +98-21-460-92320
WhatsApp/Wechat: +989123214280